

Forti-Tread

For Professional Use Only

DESCRIPTION

- A high quality, fully cured silicone sheet, reinforced with fiberglass.
- Designed to provide a long-lasting flexible membrane that will retain this flexibility even in the harshest climatic conditions.
- Formulated utilizing high quality silicone and fiberglass to create a very heat resistant and puncture resistant membrane.
- Fully compatible with the FortiSystems Forticoat Silicone line of silicone coatings and accessories.
- Can come in a variety of colors, with a minimum purchase quantity.

RECOMMENDED USES

Forti-Tread Pre-Cured Silicone Walkpads may be rolled onto wet silicone coating to fully adhere to the roof surface. This surface will then be used as a designated walkpad, designed for light foot traffic.

Property	Test Method	Result
Heat Resistance (consistent)	ASTA E-84	550 F
Heat Resistant (sparks)	ASTM E-84	1265 F
Tensile Strength	ASTM D-2370	1850 PSI
Elongation	ASTM D-2370	24.6%
Permeability	ASTM D-1653	12
Tear Resistance	ASTM D-624	440 PSI
Thickness		.9mm +/- .05
Weight		12 oz/SF
Reflectivity	ASTM C-1549	94%
Emittance	ASTM C-1371	92%
SRI	Calculated	99 (white only)

COLORS

Standard Colors: Safety Yellow

PACKAGING/SHIPPING INFORMATION

CONTAINER SIZE

1 Roll (538 SF)
1 Pallet (30 rolls)

SHIPPING CLASS

Class 55
Class 55

To the best of our knowledge all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. Used must contact Everest systems Company to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Everest Systems Products. We assume no responsibility for coverage, performance or injuries resulting from use. Liability if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY EVEREST SYSTEMS EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

SURFACE PREPARATION

General: Surface should be properly prepared with the Forticoat Silicone coating system. An additional layer of silicone should be applied to the area receiving the walkpad at a rate of 1 gallon per 100 SF. While the coating is still wet, roll the pre-cured walkpad into the wet silicone. Allow to cure for 24 hours before allowing foot traffic on the walkpad. If there are installation questions, please contact your FortiSystems representative before proceeding.

PONDED WATER

- FortiSystems warranties do not cover damage due to ponding water.
- The National Roofing Contractors Association considers ponding water on any roof unacceptable.
(See the NRCA Roofing and Waterproofing Manual).

No warranty is expressed or implied regarding the wearability, waterproofing, slip resistance or other feature of this product.

16601 Central Green Blvd Ste. 100 • Houston, TX 77032

www.FORTI-SYSTEMS.com • Phone 833-840-2777