

Clear Sealer for Masonry

For Professional Use Only

DESCRIPTION

- Excellent adhesion to masonry surfaces.
- Rapid drying water-based technology.
- Compatible with most types of top coats.
- Saves money by reducing the absorption of top coats into the substrate.
- Low VOC technology meets most VOC regulations.
- Easy to apply.

RECOMMENDED USES

FortiPrime CP provides an excellent sealer for masonry surfaces. It will improve the adhesion of coating systems and reduce excess usage of top coat materials allowing them to remain on the surface for maximum protection.

Property	Result
Total Solids	25% $\pm$ 2%
Weight per Gallon	8.6 lbs per gallon $\pm$ 0.2
VOC	100 g/liter
Clean Up	Water
Shelf Life-unopened	12 months @ 40-90°F
Viscosity	200 $\pm$ 100 cP

COLORS

Clear

PACKAGING/SHIPPING INFORMATION

CONTAINER SIZE	SHIPPING CLASS
55 Gallon drum (208.2 liters)	Class 55
5 Gallon pail (18.9 liters)	Class 55
2 Gallon pail (7.6 liters)	Class 55

SURFACE PREPARATION

The surface must be clean, dry, and free of loose particles or other foreign matter.

Masonry must be cured for at least 30 days before application.

APPLICATION

This product may be brushed rolled or sprayed on a clean, dry surface. For details see Equipment Recommendations at the end of this sheet. If sprayed, the material should be at least 50°F.

Application Properties

Yield (1 gal to 200 sq ft)	3 dry mils
Dry Time (75° F)	2 to 3 hours
Recoat window	2 to 3 hours
Complete Cure	5 days

COVERAGE RATE

Apply FortiPrime CP at the rate of 1 gallon per 200 sq. ft. (3 wet mils). Surface texture and wind will affect applied mil thickness.

Clear Sealer for Masonry

ENVIRONMENTAL CONDITIONS

This product cures by water evaporation only. The product must not be applied when the ambient temperature is below 50°F or if there is any possibility it could fall below 32°F within 24 hours of application. Application is not recommended if rain or dew is likely to occur before the product dries. In high humidity conditions, late afternoon applications should be avoided as overnight dew formation on an uncured surface can cause coating wash-off. On marginal days, multiple applications of thin coats can ensure proper drying before rain or overnight freezes.

LIMITATIONS

The surface must be clean and dry. Application is not recommended on roofs with slopes less than 1/8 in 12 or where ponded water is present. Do not apply over wet substrates or when inclement weather is imminent. Complete cure of FortiPrime CP requires complete evaporation of water. Cool temperatures and high humidity retard cure.

SAFE PRACTICES

This product is designed for professional installation. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. Information sources include but are not limited to SDS and product labels.

EQUIPMENT

Minimum requirements:

Roller

- 1¼" nap roller

Spray

- Standard Paint Sprayer is suitable

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. Users must contact Everest Systems LLC to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Everest Systems Products. We assume no responsibility for coverage, performance, or injuries resulting from use. Liability, if any, is limited to the replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY EVEREST SYSTEMS EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.