

Bleed Resistant, Base Coat for Silicones and Acrylic Top Coats

For Professional Use Only

DESCRIPTION

- A high quality, versatile plasticizer-free, single-component, water-based, acrylic elastomer basecoat for spray, brush, or roller application.
- Designed to provide a long-lasting flexible membrane with exceptional resistance to weathering.
- Formulated with "bleed resistant" materials to block the bleed-through of those asphaltic components that can discolor topcoats.
- Has excellent adhesion to most surfaces including metal, most single-ply roofs, wood, and concrete.
- Has the unique ability to "breathe", providing a completely watertight membrane while allowing trapped moisture to escape.

RECOMMENDED USES

FortiPrime Bleed Block is designed as a general-purpose coating for applications over metal, properly primed single-ply, and asphaltic surfaces such as asphalt emulsions. Check with your FortiSystems representative for primer recommendations.

Property	Test Method	Result
Volume Solids	ASTM D-1653	52.0 $\pm$ 3%
Weight Solids	ASTM D-1644	65.0 $\pm$ 3%
Tensile Strength	ASTM D-2370	310 $\pm$ 20 psi
Elongation	ASTM D-2370	315 $\pm$ 20%
Permeability	ASTM D-1653	9 $\pm$ 1
VOC	EPA Method 24	< 50 g Liter
Hardness (Shore A)	ASTM D-2240	55 - 60
Viscosity		75 $\pm$ 10 KU
Density		11.9 lbs per gallon
Flashpoint		None
Shelf Life		12 months
Clean Up		Water

COLORS

Standard Colors: White, Gray, and Tan
Custom Colors are available for an additional charge.

PACKAGING/SHIPPING INFORMATION

<u>CONTAINER SIZE</u>	<u>SHIPPING CLASS</u>
55 Gallon drum (208.2 liters)	Class 55
5 Gallon pail (18.9 liters)	Class 55

Bleed Resistant, Base Coat for Silicones and Acrylic Top Coats

SURFACE PREPARATION

General: Surfaces to be coated should be dry, free of dust, dirt, oil, loose granules, gravel, peeling coating, and other foreign matter. All wet insulation or foam should be removed and replaced with like materials.

For optimal results power wash all surfaces with a minimum of 2000 psi using a wide fan tip. All necessary precautions should be taken to avoid damage to the roof system. Mildew should be treated with a bleach solution (1 part bleach, 2 parts water) and rinsed thoroughly. Patch and repair cracks or holes with appropriate sealants or caulking materials.

APPLICATION

This product may be brushed rolled or sprayed on a clean, dry surface. For details, see Equipment Recommendations at the end of this sheet. If sprayed, the material should be at least 75°F. Before applying an additional coat, the previous coat must be completely dry and cured. If any contamination is present on the cured surface, it must be washed and completely dry before application of subsequent coats.

Application properties

Yield (1 gal to 100 sq ft)	8.3 dry mils
Dry Time (75° F)	90 mins @ 50% humidity
Recoat window	>6 hrs
Complete Cure	30 days

COVERAGE RATE

Apply **FortiPrime Bleed Block** at the rate of 1.0 gallons per 100 sq. ft. (16 wet mils). Surface texture and wind will affect applied mil thickness.

Once completely dry, **FortiPrime Bleed Block** may be top coated with Acrylic or Silicone Coating.

ENVIRONMENTAL CONDITIONS

This product cures by water evaporation only. The product must not be applied when the ambient temperature is below 50°F or if there is any possibility it could fall below 32°F within 24 hours of application. Application is not recommended if rain or dew is likely to occur before the product dries. In high humidity conditions, late afternoon applications should be avoided as overnight dew formation on an uncured surface can cause coating wash-off. On marginal days, multiple applications of thin coats can ensure proper drying before rain or overnight freezes.

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. Users must contact Everest Systems LLC to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Everest Systems Products. We assume no responsibility for coverage, performance, or injuries resulting from use. Liability, if any, is limited to the replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY EVEREST SYSTEMS EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

PONDED WATER

- FortiSystems coatings are not warranted to perform under ponding water.
- The National Roofing Contractors Association considers ponding water on any roof unacceptable. (See the *NRCA Roofing and Waterproofing Manual*).

LIMITATIONS

The surface must be clean and dry. Application is not recommended on roofs with slopes less than 1/8 in 12 or where ponded water is present. Do not apply over wet substrates or when inclement weather is imminent. Complete cure of **FortiPrime Bleed Block** requires complete evaporation of water. Cool temperatures and high humidity retard cure. In addition, this product is not recommended for use without a vapor barrier in cryogenic tank or cold storage roofing applications. It is not intended as a thermal barrier.

SAFE PRACTICES

This product is designed for professional installation. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. Information sources include but are not limited to MSDS and product labels. More resources are available at polyurethane.org, sprayfoam.org, www.forti-systems.com, or by contacting your FortiSystems representative directly.

EQUIPMENT

Minimum requirements:

Brush

- Synthetic filament

Roller

- 1 1/4" nap roller

Spray

- 30:1 fluid-to-air ratio capable pump
- 2 1/2 gallons or more per minute (continuous)
- Filter screen 30 mesh or larger
- Hose rated to 2x maximum pump pressure
- Hose lining should be compatible with coating and required cleanout materials
- Hose lengths: (Largest diameter at pump)
 - 3/8 minimum 6 ft wip
 - 3/8 minimum I.D. up to 75 feet
 - 1/2 minimum I.D. up to 200 feet
 - 3/4 minimum I.D. over 200 feet
- Spray gun: Graco Hydra Mastic or equivalent
- Spray Tip:
 - Reversible self-cleaning type
 - Orifice size of .027 to .039
 - Fan angle of 40° to 50°
- Always use components rated for pump pressures